



NORCOAT® LIÈGE HPK

THERMAL PROTECTION PRODUCT LINE

- > **NORCOAT® LIÈGE HPK**
- > NORCOAT® 4000
- > NORCOAT® 4011
- > NORCOAT® 5011
- > PROSIAL® 2000
- > ASTERM®
- > NORCOAT® FLEX
- > NAXECO® PYC
- > NAXECO® RESIN

CORK BASED ABLATIVE THERMAL PROTECTION



NORCOAT® LIÈGE HPK

CORK BASED ABLATIVE THERMAL PROTECTION

ArianeGroup has been developing and manufacturing thermal protection for space applications for over 40 years and is recognized as an European leader. Our range of manufacturing processes allows many designs to protect the structures: bonding, moulding or spraying.

| CHARACTERISTICS | |
|------------------------------|--|
| Density | 0.47 |
| Thermal Conductivity at 20°C | 0.09 W·m ⁻¹ ·K ⁻¹ |
| Specific heat at 150°C | 1.8 kJ·kg ⁻¹ ·K ⁻¹ |
| Tensile stress | 0.7 MPa |
| Elongation | 6% |
| Dimensions | 1210 mm x 680 mm |
| Thickness | 1 to 120 mm |
| Heat flux | 2 MW/m ² |

NOTE:
Data in this document is for information purposes only.

Our product:

- **Easily Machinable:**
Available in plates, or pre-cut kitting (2D) or in shape (3D)
- **High thickness** available
- **Fungicide included (F):**
No shelf life–stability over time
- **Fire proof (FI)**
- **Water repellent (FIH)**
- **Defence and Space qualified:**
Ariane 5, Mars entry, Ariane 6 ready, Military launchers
- Can be **coated** (Antistatic paint e.g.)
- **Composite** and **Metallic** substrates
- **2000°C** material



ADVANTAGES

Excellent heat performances

Material adaptability

- Thin-skin is ideal for confined spaces
- Lightweight materials

Manufacturing process adaptability

Material stability

- Mechanical stability: materials paired with all support types
- Stability over time: 20-year life cycle for temperatures of between -50°C and 200°C

Fully adapted solutions

- Need analysis
- Material definition and manufacturing
- Technical product support
- Durable supply with adaptation to new standards

CONTACT

EMILIE LIEBENS

Email: emilie.liebens@ariane.group

Phone: +33 5 56 57 25 39

www.ariane.group

ArianeGroup SAS

Site d'Issac

Rue du Général Niox, BP 30056

33166 Saint-Médard-en-Jalles

France